


EPORITE



EPORITE EHM-83

GENERAL

EPORITE EHM-83 series is a one-component epoxy hot melt system recommended especially for fiber-reinforced prepreg.

The cured EPORITE EHM-83 exhibits excellent physical properties such as mechanical strength, and heat stability.

STORAGE

Store EPORITE EHM-83 at temperature lower than 5°C.

HANDLING AND SAFETY

Gloves and glasses are suggested for user's personal protection. Clean with soap and water when skin contact.

PROCESSING

1. Coating process: 70 ~ 75°C
2. Impregnation process: 100 ~ 105°C
3. Storage: lower than 5°C
4. Molding process: 90 ~ 100°C / 0.5 hr + 150°C / 1.5 hr.

*All of above temperatures are suggested temperatures.

NOTE: The process can be adjusted according to the specific manufacturing process or performance requirement.

SPECIFICATION

Specification	EPORITE EHM-83
Chemical Type	Epoxy Compound
Appearance	White solid
Specific Gravity	1.2 ± 0.1
Viscosity (70°C)	150000 ± 37500 cps
Shelf Life	6 months (5°C) or 1 month (25°C)
Gel Time (150°C)	< 7 min/0.2g
Curing Condition	90 ~ 100°C / 0.5 hr + 150°C / 1.5 hr

PROPERTIES OF THE CURED RESIN

Property	EPORITE EHM-83
Glass Transition Temperature (°C)	115 ~ 135
Flexure Strength (N/mm ²) (25°C)	> 120
Young's Modulus (Mpa) (25°C)	> 3250

REMARK

The information contained is believed to be reliable and only for the reference without any effective guarantee for the application of the user. The user is responsible to determine the suitability for the user's application and the reliability of the products. Epolab Chemical will not accept claim of warranties of the fitness or reliability for a particular purpose especially the liability for consequential damages of end products.



EPOLAB CHEMICAL INDUSTRIES INC.

No. 11, Ho-Jiun N. Rd., Chung-Li Ind. Park, Chung-Li, Taoyuan 320, Taiwan

Tel : 886-3-4521501~3 Fax : 886-3-4529318 service@epolab.com.tw www.epolab.com